

# Replacement Elements Media

<b>Dura-Life®</b>	
<b>Appearance</b>	White
<b>Use</b>	Filter bags
<b>Composition</b>	100% polyester
<b>Area weight</b> (DIN 53854)	340 g/m <sup>2</sup>
<b>Thickness</b> (DIN 53855)	1.6 mm
<b>Air permeability</b> (DIN 53887)	170 l/dm <sup>2</sup> min @ 200 Pa
<b>Dimensional stability @ 177°C</b>	<3.0%
<b>Surface finish</b>	None
<b>Additional treatments</b>	Heat set
<b>Surface electrical resistance</b>	Not applicable
<b>BIA category</b>	Not applicable
<b>Temperature</b> (dry heat)	
Continuous	135°C
Peaks	150°C
<b>Chemical resistance</b>	
Hydrolysis	Poor
Acids	Good
Alkalis	Good
Oxidising agents	Very good
Organic solvents	Very good
<b>Abrasion resistance</b>	Very good
<b>Supports combustion</b>	Yes
<b>Application field</b>	Dura-Life is suitable for the majority of temperature and chemical environments normally encountered in Dalomatic applications including acidic and weak alkaline conditions at ambient temperature.

