

Replacement Element Media

Ultra-Web®	
Appearance	Blue tinted, corrugated
Use	Pleatable filter media
Composition	Cellulose substrate with nanofiber layer
Area weight (DIN 53884)	114 g/m ²
Thickness (DIN 53885)	0,28 mm
Air Permeability (DIN53887)	400 m ³ /m ² .h at 200 Pa
Dimensional stability	N/A
Surface finish	N/A
Additional treatments	N/A
Surface electrical resistance (DIN 54345)	4,5 x 10 ⁹ Ohm
BIA Category (DIN 60335-2-69)	Class M Test report Nr. 200423074/6210
Temperature (dry heat)	
Continuous	65°C
Peaks	80°C
Chemical resistance	
Hydrolysis	N/A
Acids	Poor
Alkalis	Fair
Oxidising Agents	Poor
Organic Solvents	Fair
Abrasion Resistance	Good
Supports Combustion	Yes
Application field	Premium performance on ambient, extremely fine and non-fibrous dust and some abrasive dust. High filtration efficiency on very fine particulate of <1 micron. Typical applications include metallisation, laser cutting, pharmaceuticals, weld fume, shot blasting...

Replacement Element Media



www.donaldson.com

Humberstone Lane
Thurmaston
Leicester LE4 8HP
England

Tel +44 (0)116 269 6161
Fax +44 (0)116 269 3028

Email: IFS-uk@emea.donaldson.com

Research Park Zone 1
Interleuvenlaan 1
B-3001 Leuven (Heverlee)
Belgium

Tel +32 (0)16 383 970
Fax +32 (0)16 383 938

Email: IFS-europe@emea.donaldson.com